

Titanium Ingot Specifications	Al %	Zr	Mo	V %	Fe %	Mn %	Sn %	Si %	S %	P %	O %	C %	N %	H %	Ti %
Met 211, 6-4 Titanium	5.50 - 6.50	-	-	3.50 - 4.50	0.40	-	-	-	-	-	0.20	0.08	0.05	0.015	Bal
Met 212, 6-2-4-2 Titanium	6.00	4.00	2.00	-	0.05	-	2.00	-	-	-	0.20	0.10	0.04	0.015	Bal
Met 221, CP Grade 4 Titanium	-	-	-	-	0.50	-	-	-	-	-	0.40	0.08	0.05	0.015	Bal
Met 231, CP Grade 3 Titanium	-	-	-	-	0.30	-	-	-	-	-	0.35	0.08	0.05	0.015	Bal
Met 241, CP Grade 2 Titanium	-	-	-	-	0.30	-	-	-	-	-	0.25	0.08	0.03	0.015	Bal
Met 251, CP Grade 1 Titanium	-	-	-	-	0.20	-	-	-	-	-	0.18	0.08	0.03	0.015	Bal